



<b>MATERIAL</b>	Viton™ 75 Shore FDA and 3 A Class 1 Black ASTM D 2000 M2HK 710 B38 C12 Z1 75° +/-5 ShA	
<b>DESCRIPTION</b>	Low compression set Viton™ O ring grade Copolymer with 66% fluorine content Cure system is Bisphenol FDA compliant to CFR 21 177-2600 E & F & European regulations EC1935/2004 This compound has been tested following the standard (EC) 1935/2004 and according to (EU) 10/2011	
<b>APPLICATION</b>	This material has excellent resistance to oils, fuels, lubricants, most mineral acids aliphatic and aromatic hydrocarbons.	
<b>TEMPERATURE</b>	Low temperature service limit -4°F (-20°C) Upper temperature continuous service limit +400°F (+204°C)	
<b>PRODUCTS</b>	Encapsulated Seals Hot Vulcanised O rings & Profiles	Extrusions (cords/profiles/tubes) Moulding (custom/O rings)

## PHYSICAL PROPERTIES

ORIGINAL	STANDARD	TYPICAL VALUES
Specific Gravity	ASTM D1817	2.32
Durometer shore A (slab)	ASTM D2240	79
Elongation % (Dumbbell)	ASTM D412	233
Tensile strength PSI (MPa) (Dumbbell)	ASTM D412	1672 (11.52)
Modulus @ 100%	ASTM D945	7.2
Compression set % 22h @ 347°F (175°C) (slab)	ASTM D395B	4.6
22h @ 400°F (200°C)		7.0
Low temperature TR-10°F (°C)*	ASTM D1329	1.4 (-17)

\*Nominal value based on typical 75 shore vulcanizate

### HEAT AGEING 70h @ 482°F (250°C) ASTM D573

Durometer change points shore A	+4
Elongation change %	-34
Tensile strength change PSI (MPa)	+537 (+3.7)
Weight loss %	-0.02

### FLUID IMMERSION Oil No 3 70h @ 302°F (150°C) ASTM D471

Volume change %	+4.56
Durometer change points shore A	0.5
Elongation change %	-6.5
Tensile strength change PSI (MPa)	+68 (+0.47)

### FLUID IMMERSION Fuel C 70h @ 73°F (23°C) ASTM D471

Volume change %	+3.0
Durometer change points shore A	-1
Elongation change %	-3
Tensile strength change PSI (MPa)	-32 (-0.22)

### OZONE RESISTANCE 70h @ 104°F (40°C) (50pphm) ASTM D1171

Result	Pass
--------	------

### TEAR STRENGTH ACCORDING TO ISO 34-2

Value	40 N
-------	------



Information  
The above information corresponds to our current knowledge and is offered solely to provide possible suggestions for your own experiments. It is not intended to substitute any testing you may need to conduct to determine suitability of our products for your end use. Northern Engineering reserves the right to revise this information as new knowledge and experience becomes available. Northern Engineering makes no warranties and assumes no liability in connection with any use of the above information.