NES Material Data Sheet MC314 EPDM 70 Shore FDA/USP Black

Aug-2024 Revision: 8

| MATERIAL | EPDM 70 Shore FDA & USP Class VI <88> Black ASTM D 2000 M2CA 810 A25 |
|-------------|---|
| DESCRIPTION | EPDM is a polymer of ethylene, propylene and a small amount of diene Cure system is peroxide FDA compliant to CFR 21 177-2600 and European regulations EC 1935/2004 |
| APPLICATION | EPDM's have good resistance to ozone, ageing and weathering. They are suitable for HFC & HFD flame retardant hydraulic oils and brake fluids and have exceptional resistance to hot water, steam and acids. Approved to USP Class VI, is USP biological reactivity tested in vivo <88> and extraction tested at 121°C and is FDA compliant to CFR 21 177-2600 and European regulations EC 1935/2004. Approved to USP Class VI, USP biological reactivity tested in vitro <87> and is considered to have no cytotoxic potential. |
| TEMPERATURE | Low temperature service limit -40°F (-40°C) Upper temperature continuous service limit +284°F (+140°C) |
| PRODUCTS | Moulding (custom/O rings) |

PHYSICAL PROPERTIES

| VIILO | | | |
|--|--------------|----------------|--|
| ORIGINAL | STANDARD | TYPICAL VALUES | |
| Specific Gravity | ASTM D1817 | 1.14 | |
| Durometer shore A (slab) | ASTM D2240 | 73 | |
| Elongation % (Dumbbell) | ASTM D412 | 299 | |
| Tensile strength Psi (Mpa) (Dumbbell) | ASTM D412 | 1885 (13.0) | |
| Compression set % 22h @ 212°F (100°C) (slab) | ASTM D395B | 9.4 | |
| HEAT AGEING 70h @ 212°F (100°C) ASTM D573 | | | |
| Durometer change points shore A | +4 | | |
| Elongation change % | +24 | | |
| Tensile strength change Psi (Mpa) | -87 (+0.6) | | |
| Weight loss % | | 1.7 | |
| FLUID IMMERSION Oil No 3 70h @ 212°F (100°C) ASTM D471 | | | |
| Volume change % | | +120 | |
| Durometer change points shore A | -31 | | |
| Elongation change % | -174 | | |
| Tensile strength change Psi (Mpa) | -726 (-5.0) | | |
| ANTI-STATIC PROPERTIES - 80-100 kOhm THROUGH A 2MM SHEET USING A MEGGER AT <2 VOLT | | | |
| Conductivity kOhm on 2mm sheet | Megger 100 V | 80-100 | |
| | | | |

Information

The above information corresponds to our current knowledge and is offered solely to provide possible suggestions for your own experimentations. It is not intended to substitute any testing you may need to conduct to determine suitability of our products for your end use. Northern Engineering reserves the right to revise this information as new knowledge and experience becomes available. Northern Engineering makes no warranties and assumes no liability in connection with any use of the above information.



Tel: +44 (0) 1909 560 203 Fax: +44 (0) 1909 560 184 Email: sales@nes-ips.com Web: www.nes-ips.com